

USSN 10/581,373 field 7 March 2008
 Attorney Docket 6162555-0004
 Page 3 of 13

RECEIVED
 CENTRAL FAX CENTER


FEB 11 2009

AMENDMENT TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended) A fresh concrete comprising containing cement, and aggregate, water and an admixture, wherein the admixture comprises: admixtures with

- (a) a mixture of (i) sodium sulfate, (ii) sodium salt of lignosulfonic acid and (iii) sodium salts of polymethylene naphthalenesulfonic acids of the general formula



where n is 1 to 25; superplasticizer C 3;

- (b) an antifoaming agent comprising a silicone emulsion; hydrophobing agent and
(c) a modified lignosulfonate Lignopan B having the molecular weight of 10 50 kJ;

[[L]]

characterized by antifoam as hydrophobing agent (139-282)

- (d) one or more compounds selected from the group consisting of and fixing salt and/or ammonium thiocyanate, and/or sodium thiocyanate and and/or sodium sulfate, and

- (e) sodium carbonate having the following ratio of components (parts by mass):

superplasticizer C 3	0-40
the hydrophobing agent indicated	0.02-0.06
the Lignopan B indicated	10-20

USSN 10/581,373 filed 7 March 2008
 Attorney Docket: 6169555-0004
 Page 4 of 13

~~fixing salt and/or ammonium thiocyanate and/or sodium and/or~~
~~sodium sulfate~~ _____ 40-55
~~sodium carbonate~~ _____ 1-2,

~~having a content of the admixture of 0.6-1.5 parts by mass of the cement mass.~~

2. (Currently amended) The fresh concrete as claimed in claim 1, wherein the amount of each of the cement, aggregate and water is within the following range characterized in that it contains the components indicated in the following ratio:

cement	300-500 kg/m ³
aggregate	1590-2030 kg/m ³
water	105-200 kg/m ³ .

3. Canceled The fresh concrete as claimed in claim 1 or 2, characterized in that it contains coarse and/or fine aggregate.

4. Canceled The fresh concrete as claimed in claim 3, characterized by gravel and/or construction sand as coarse aggregate.

5. (Currently amended) The fresh concrete as claimed in claim 1, wherein the aggregate is a ~~claim 3 or 4, characterized by coarse aggregate having a~~ particle size of 5-20 to 5-40 mm

6. (Currently amended) The fresh concrete as claimed in claim 1, wherein the aggregate is a fine aggregate ~~any of claims 3 to 5,~~ characterized by sand having a particle the size of not more than 5 mm as fine aggregate.

7. (Currently amended) The fresh concrete as claimed in claim 6, wherein the fresh concrete comprises one or more ~~any of claims 3 to 6,~~ characterized by at least one component of the ~~following group as~~ fine aggregate selected from the group consisting of ~~[[.]]~~ quartz sand, eruptive rock sand, metamorphic sand, expanded clay sand ~~[[.]]~~ and iron slag sand.